

Komposisi kimia tungsten

menandakan		WB-1	WB-2	WB-3	WB-4	tipikal -1	tipikal -2
berhadaskan maksimum %,	Pb	--	--	--	0.001	--	0.001
	Bi	--	--	--	0.001	--	0.001
	Sn	--	--	--	0.001	--	0.001
	As	--	--	--	0.002	--	0.001
	Fe	0.005	0.005	0.010	0.05	0.005	0.020
	Ni	0.003	0.003	0.005	0.30	0.002	0.005
	Al	0.002	0.002	0.005	0.005	0.001	0.003
	Si	0.003	0.003	0.010	0.010	0.0015	0.002
	Ca	0.003	0.003	0.005	0.005	0.002	0.005
	Mg	0.002	0.002	0.005	0.010	0.001	0.001
	Mo	0.010	0.010	0.20	0.20	0.003	0.050
	P	0.001	0.001	0.002	0.005	0.001	0.001
	C	0.005	0.008	0.010	0.010	0.003	0.003
	O	0.003	0.003	0.005	0.008	0.003	0.008
	N	0.003	0.003	--	--	0.003	--
Sb	--	--	--	0.001	--	0.0005	
menggunakan	aloi tungsten	material Processing	material Processing	tambah aloi	material Processing	tambah aloi	

Nota: Semua spesifikasi produk mengikuti kehendak pelanggan yang lain.